

## Starcret universal filler



Ready-to-use cement-based dry mix, plastic-modified. For repairs, coatings and for smoothing, levelling concrete, plaster and mortar. Especially for exposed concrete cosmetics for interior and exterior use. Grain size 0 - 0.3 mm

High flexural strength (see strength tables)  
Consistent quality and colour (concrete light, without colour pigments)

### Consumption

Consumption:

15 kg dry mortar yields approx. 7.5 litres fresh mortar.  
Layer thickness 1.5 - 5 mm per working step

### Processing

Processing:

The substrate must be cleaned and pre-wetted.  
The water requirement is approx. 3.3 l per 15 kg bucket.  
Mix until a spatula-like consistency is achieved.  
Processing time approx. 60 minutes at 20°C

### Technical data

Strength tables

1 day 3 days 7 days 28 days  
Compressive strength N/mm<sup>2</sup> 5.8 21 28  
Flexural strength N/mm<sup>2</sup> 1.9 3.7 5.8

Article description	Title of variant	Packaging piece/pallet	Weight kg/bucket
19027015	Starcret universal filler	1-24 bucket/pallet	15