

Grouting mortar



Ready-to-use cement-based dry mix. Self-levelling and non-shrinking.

For void-free underpouring/grouting of foundation slabs, machine frames, precast concrete parts, anchors, bridge bearings, manhole covers and similar. Not suitable for surface grouting.

High flexural strength
Resistant to frost and de-icing salt

Consumption

Consumption:

25 kg dry mortar yields 13 litres grout

Processing

Processing:

Water requirement approx. 3.5 l per 25 kg depending on flowability.

Mixing time between 4 - 6 minutes

Working time approx. 60 minutes at 20°C

Article description	Title of variant	Casting height mm	Packaging piece/pallet	Weight kg/piece
19025010	Grouting mortar	until 20	1-42 bag/pallet	25
19025040	Grouting mortar	20 - 100	1-42 bag/pallet	25